

JLON-4025

PTFE, 25% Glass Fill



TECHNICAL DATA

PROPERTY	ASTM METHOD	VALUE
Specific Gravity	D792	2.22
Tensile Strength	D4894	2390 PSI
Elongation @ Break	D4894	215%
Compressive Modulus	D695	62000 PSI
Compressive Strength @ 0.2% Offset	D695	1040 PSI
Compressive Strength @ 5% Strain	D695	2760 PSI
Hardness	D2240	60 - 66 Shore D