

J-4100 *Rulon Comparable: AR*



TECHNICAL DATA

PROPERTY	ASTM METHOD	VALUE
Specific Gravity	D792	2.23
Tensile Strength	D4894	3,000 psi
Elongation @ Break	D4894	285%
Compressive Modulus	D695	61,000 psi
Compressive Strength @ 0.2% Offset	D695	1,060 psi
Compressive Strength @ 5% Strain	D695	1,730 psi
Hardness	D2240	58-64 Shore D