

J-4200 *Rulon Comparable: LR*



TECHNICAL DATA

PROPERTY	ASTM METHOD	VALUE
Specific Gravity	D792	2.24
Tensile Strength	D4894	2,620 psi
Elongation @ Break	D4894	225%
Compressive Modulus	D695	63,000 psi
Compressive Strength @ 0.2% Offset	D695	1,100 psi
Compressive Strength @ 5% Strain	D695	1,810 psi
Hardness	D2240	60-65 Shore D